



**Kisling AG**

**Motorenstrasse 102  
CH-8620 Wetzikon**

Telefon +41 (0)58 272 01 01  
Telefax +41 (0)58 272 01 03

info@kisling.com  
www.kisling.com

## TECHNICAL DATA SHEET

### ergo® 6200/ 6201/ 6205 Hybrid-Polymer

Fast curing, elastic single-component sealant and adhesive for bonding as well as sealing of seams and joints in carbody-, waggon-, container and boatbuilding.  
Also suitable for mechanical engineering and applications in air-conditioners and ventilation technologies.

#### Advantages

- good adhesion to glass, a wide range of metal (zinc, aluminium, steel), varnished and primed surfaces
- good adhesion to wooden as well as to mineral substrates and to thermoplastics (except PE, PP, PTFE)
- resistant against humidity, weathering and temperatures from -40°C up to +90°C (up to +120°C for short intervals)

#### Properties of liquid product

Chemical Base	Hybrid-Polymer
Appearance	pasty, spreadable with a blade, stable
Colour	ergo® 6200 ergo® 6201 ergo® 6205
	white grey black
Density at 23°C	~ 1,44 g/cm <sup>3</sup>
Skinning time at 23°C/50%rh	~ 10 minutes
Curing progress at 23°C/50%rh	after 24 h : 3 mm
Change of weight (after 14 days)	~ 1 %

#### Typical properties of cured product

Tensile strength (DIN 53504) storage 7 days at 23°C/50%rh	~ 3,0 N/mm <sup>2</sup>
Elongation at break (DIN 53504) storage 7 days at 23°C/50%rh	~ 500 %
Modulus at 100% elongation and 23°C (DIN 53504 S2) storage 7 days at 23°C/50%rh	~ 1,0 N/mm <sup>2</sup>
Tear resistance (ASTM D 624, Form B) storage 7 days at 23°C/50%rh	~ 20 N/mm



**Kisling AG**

**Motorenstrasse 102  
CH-8620 Wetzikon**

Telefon +41 (0)58 272 01 01  
Telefax +41 (0)58 272 01 03

info@kisling.com  
www.kisling.com

- 2 -

Shore-A-hardness (DIN 53505)  
storage 28 days at 23°C/50%rh

~ 42

Thermal range

-40°C up to +90° C  
(short intervals up to +120°C)

Working temperature

+5°C bis +30°C

Packaging

cartridges à 310 ml

Storage conditions

cool (no longer periods > +25°C)  
and dry

Storage stability

15 month in original box

## Usage

Good adhesion to clean, dry and grease-free surfaces (cleaned either with **ergo® 9190** or **ergo® 9195**), even without Primer. For best results we recommend the use of Primer ergo® 6950 (non absorbing surfaces) or of Primer ergo® 6960 (absorbing surfaces)  
Please check the compatibility with varnish and plastic in advance

Apply ergo® 6200/ 6201/ 6205 with a common putty gun. The thickness of the needed layer depends on expected forces and relative movements.

The curing process is influenced by layer thickness, temperature and humidity

## Safety

Please read our MSDS and the labels carefully before use

### WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KISLING products are safe, effective, and fully satisfactory for the intended end use. KISLING sole warranty is that the product will meet the KISLING sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. KISLING specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KISLING provides you with a specific, duly signed endorsement of fitness for use, KISLING disclaims liability for any incidental or consequential damages. Suggestions of uses should not be taken as inducements to infringe any particular patent.